



TECHNICAL DATA SHEET

Order reference	GP100-M
Article number	813812

Date	4-11-11	Replaces	3-27-07	No. Pages	1
-------------	---------	-----------------	---------	------------------	---

Product Description:

Style	Pads; perforated on centerline for dividing in half for smaller applications
Item Size (each)	41 cm x 51 cm
Color	Gray
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	A nonwoven mat of randomly oriented Micro-fibers [2-10 micron diameters]
Technology	Meltblown
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	--

Absorbency Capacity	95 l per box (saturated; medium viscosity-14x)
----------------------------	--

Packaging Description:

Package configuration	Case	Pkg. Weight	7,1 kg (5,9kg)
Items per Package	100-Pads/Case	Pkg. Dimensions	53 cm x 43 cm x 44 cm H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	275	27
Caliper	SPCTM-020	mm	5	0.5
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	14	2
Tensile strength	SPCTM-007	daN	6,3	0.6
Color	Visual	-----	Gray	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.